

Mar8"CharacterNameWidthGrade

DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Baltic Birch Plywood and European White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	9/16" (14mm)
Top Layer thickness (mm)	3 mm (nominal)
Plywood thickess (mm)	11 mm
Length (ft)	6-8'
Width (in)	8"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length



GRADE

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com













Cielo8"CharacterNameWidthGrade

DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Baltic Birch Plywood and European White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	9/16" (14mm)
Top Layer thickness (mm)	3 mm (nominal)
Plywood thickess (mm)	11 mm
Length (ft)	6-8'
Width (in)	8"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length



GRADE

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com















Sol8"CharacterNameWidthGrade

DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Baltic Birch Plywood and European White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	9/16" (14mm)
Top Layer thickness (mm)	3 mm (nominal)
Plywood thickess (mm)	11 mm
Length (ft)	6-8'
Width (in)	8"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length



GRADE

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com













8" Character Arena Name Width Grade

DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Baltic Birch Plywood and European White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	9/16" (14mm)
Top Layer thickness (mm)	3 mm (nominal)
Plywood thickess (mm)	11 mm
Length (ft)	6-8'
Width (in)	8"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length



GRADE

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com















Monte8"CharacterNameWidthGrade

DESCRIPTION

This product has been manufactured according to the European Norm EN13489. Product: Multilayer Parquet Oak Plank.

COMPOSITION

Structure consists of a Baltic Birch Plywood and European White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

DIMENSIONS

Total thickness (in)	9/16" (14mm)
Top Layer thickness (mm)	3 mm (nominal)
Plywood thickess (mm)	11 mm
Length (ft)	6-8'
Width (in)	8"

DIMENSIONS TOLERANCES (EN 13647)

Length	Nominal ± 0.1%
Width	Nominal ± 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length



GRADE

Finished	Bona® Ultra Matt Lacquer
Impact Resistance	Ø medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement ≤ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	ΔLw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	www.rivaspain.com
Maintenance Instructions	www.rivaspain.com









