

Mar **5 3/4"**  
Name Width

Select  
Grade

## DESCRIPTION

Product: Multilayer Parquet Oak Plank.



## COMPOSITION

Structure consists of a Baltic Birch Plywood and White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

## DIMENSIONS

Total thickness (in)	5/8" (15mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	11 mm
Fixed Length	29.1"
Width (in)	5 3/4"

## DIMENSIONS TOLERANCES

Length	Nominal $\pm$ 0.1%
Width	Nominal $\pm$ 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

## GRADE

Select. Minimal knots. Maximum diameter of 10 mm and repaired with filler. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Germany Treffert Lacquer
Impact Resistance	$\varnothing$ medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement $\leq$ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	$\Delta Lw$ : 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	<a href="http://www.rivaspain.com">www.rivaspain.com</a>
Maintenance Instructions	<a href="http://www.rivaspain.com">www.rivaspain.com</a>



Cielo      **5 3/4"**      Select  
Name      Width      Grade

## DESCRIPTION

Product: Multilayer Parquet Oak Plank.



## COMPOSITION

Structure consists of a Baltic Birch Plywood and White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

## DIMENSIONS

Total thickness (in)	5/8" (15mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	11 mm
Fixed Length	29.1"
Width (in)	5 3/4"

## DIMENSIONS TOLERANCES

Length	Nominal $\pm$ 0.1%
Width	Nominal $\pm$ 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

## GRADE

Select. Minimal knots. Maximum diameter of 10 mm and repaired with filler. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Germany Treffert Lacquer
Impact Resistance	$\varnothing$ medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement $\leq$ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	$\Delta Lw$ : 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	<a href="http://www.rivaspain.com">www.rivaspain.com</a>
Maintenance Instructions	<a href="http://www.rivaspain.com">www.rivaspain.com</a>



Sol Name **5 3/4"** Width Select Grade

## DESCRIPTION

Product: Multilayer Parquet Oak Plank.



## COMPOSITION

Structure consists of a Baltic Birch Plywood and White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

## DIMENSIONS

Total thickness (in)	5/8" (15mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	11 mm
Fixed Length	29.1"
Width (in)	5 3/4"

## DIMENSIONS TOLERANCES

Length	Nominal $\pm$ 0.1%
Width	Nominal $\pm$ 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

## GRADE

Select. Minimal knots. Maximum diameter of 10 mm and repaired with filler. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Germany Treffert Lacquer
Impact Resistance	$\varnothing$ medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement $\leq$ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	$\Delta$ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	<a href="http://www.rivaspain.com">www.rivaspain.com</a>
Maintenance Instructions	<a href="http://www.rivaspain.com">www.rivaspain.com</a>





**Arena** **5 3/4"**  
Name Width

Select  
Grade

## DESCRIPTION

Product: Multilayer Parquet Oak Plank.

## COMPOSITION

Structure consists of a Baltic Birch Plywood and White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

## DIMENSIONS

Total thickness (in)	5/8" (15mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	11 mm
Fixed Length	29.1"
Width (in)	5 3/4"

## DIMENSIONS TOLERANCES

Length	Nominal $\pm$ 0.1%
Width	Nominal $\pm$ 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

## GRADE

Select. Minimal knots. Maximum diameter of 10 mm and repaired with filler. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

<b>Finished</b>	Germany Treffert Lacquer
<b>Impact Resistance</b>	$\varnothing$ medium of deep 8.59 mm
<b>Dimensional Stability (EN-1910):</b>	Movement $\leq$ 0.29%
<b>Formaldehyde Emission (EN-120)</b>	EO. CARB2 Comply
<b>Thermal conductivity (UNE-92-202)</b>	0.14W/moK
<b>Noise &amp; Impact Isolation (UNE-EN-ISO 140-8)</b>	$\Delta Lw: 17$ dB
<b>Fire Reaction (UNE 23727)</b>	Cfl-S1
<b>Profiling System</b>	Tongue & Groove, beveled 2 sides
<b>Warranty</b>	<a href="http://www.rivaspain.com">www.rivaspain.com</a>
<b>Maintenance Instructions</b>	<a href="http://www.rivaspain.com">www.rivaspain.com</a>



Monte **5 3/4"**  
Name Width

Select  
Grade

## DESCRIPTION

Product: Multilayer Parquet Oak Plank.



## COMPOSITION

Structure consists of a Baltic Birch Plywood and White Oak, both elements glued with polyvinyl acetate adhesives, in accordance to the qualification CARB2.

## DIMENSIONS

Total thickness (in)	5/8" (15mm)
Top Layer thickness (mm)	4 mm (nominal)
Plywood thickness (mm)	11 mm
Fixed Length	29.1"
Width (in)	5 3/4"

## DIMENSIONS TOLERANCES

Length	Nominal $\pm$ 0.1%
Width	Nominal $\pm$ 0.2%
Cupping	0.2% of nominal width
Banana	0.1% nominal length

## GRADE

Select. Minimal knots. Maximum diameter of 10 mm and repaired with filler. Repaired cracks or splits within the planks are not permitted. No filled cracks/splits on the ends of the planks. Natural color variation is to be expected. Sapwood may be present and allowed if the color blends into the plank. No bleached sapwood allowed.

Finished	Germany Treffert Lacquer
Impact Resistance	$\varnothing$ medium of deep 8.59 mm
Dimensional Stability (EN-1910):	Movement $\leq$ 0.29%
Formaldehyde Emission (EN-120)	EO. CARB2 Comply
Thermal conductivity (UNE-92-202)	0.14W/moK
Noise & Impact Isolation (UNE-EN-ISO 140-8)	$\Delta$ Lw: 17 dB
Fire Reaction (UNE 23727)	Cfl-S1
Profiling System	Tongue & Groove, beveled 2 sides
Warranty	<a href="http://www.rivaspain.com">www.rivaspain.com</a>
Maintenance Instructions	<a href="http://www.rivaspain.com">www.rivaspain.com</a>

